



PACIFIC POLYMERS **SUPERCURE AL** **COLD WEATHER CATALYST**

1. PRODUCT NAME **SUPERCURE AL**

2. MANUFACTURER

ER SYSTEMS (An ITW Company)
12271 Monarch Street
Garden Grove, CA 92841
Tel: 1-800-888-8340
Fax: 714- 898-5687

3. PRODUCT DESCRIPTION

SUPERCURE AL is a curing agent for polyurethane top coats manufactured by ER SYSTEMS. It will help to accelerate both tack free time and cure time.

SUPERCURE AL is designed to be used with:

- ELASTO-GLAZE 6001AL-HT (VOC)
- ELASTO-GLAZE 6001AR

Limitations: Do not add the accelerator in excess of what is required. Adding the accelerator will reduce the work life of the product. **SUPERCURE AL** is moisture sensitive. Do not leave open container expose to moisture or direct sunlight.

Shelf Life: 1 year @ 77°F (25°C) when stored in dry cool location.

Color: Clear to Light Yellow

Sizes: Quarts only

4. TECHNICAL DATA

(See below)

5. MIXING INSTRUCTION

- Add 1-quart **SUPERCURE AL** to a 5-gallon pail of the product suggested above. Note: Some applications of Topcoat may require that only a few ounces to a pint may do the job.
- Mix immediately. Mixing is best achieved with a slow

speed, heavy-duty drill (250 - 400 RPM) for two to three minutes, using a Jiffy mixing paddle.

- Apply the material immediately using a squeegee followed by a back-roll, a roller, spray and/or a brush. Use a thin nap roller to avoid thick applications.
- Do not add more than one QUART per pail.
- Caution! Improper mixing can leave stained spots on the surface of the basecoat. Once catalyst is added in the 5-gallon membrane container, it will start to react. Hence immediate mixing is required to avoid gelation and skinning.

6. AVAILABILITY AND COST

SUPERCURE AL is supplied through building material dealers. Prices vary with quantity and packaging. Quotations are made upon request.

These products are designed and manufactured to be installed by professional installers familiar with surface preparation and application procedures. All others should consult a professional installer; those who choose to install these products without professional assistance do so at their own risk.

7. PRODUCT WARRANTY

Satisfactory results depend not only upon quality products but also upon factors beyond our control; methods of application and site conditions are examples of such factors and can affect product performance. This warranty consequently extends only to products installed in strict accordance with the manufacturer's specifications. It is the user's responsibility to satisfy himself, by his own information and tests, of the suitability of the product for his own intended use; user assumes all risk and liability resulting from his use of the product. The substrate to which the product is applied must be sound structurally and otherwise.

Structural or substrate failures or imperfections resulting in damage to or failure of the product are not covered by this warranty. Since the use of the product is beyond the control of the manufacturer, the manufacturer assumes no liability for misapplication and misuse of the product.

This warranty does not cover consequential damages, nor does it cover the labor attendant to replacing product in the event of a product failure. The warranty only extends to replacement of the product itself.

All products proven to be defective in manufacture will be replaced at no charge. Since the use of these products is beyond our control we cannot assume any risk or liability for results did not obtain, nor can we accept damages in excess of the purchase price of these products.

8. MAINTENANCE

If the polyurethane membrane is damaged, it can be repaired by cleaning the surface with Acetone and recoating. A primer may be required in some applications.

9. TECHNICAL SERVICES

Technical assistance can be obtained by contacting:

ER SYSTEMS (An ITW Company)
12271 Monarch Street
Garden Grove, CA 92841
Tel: 1-800-888-8340
Fax: 714-898-5687

POTLIFE / TACKFREE / LIGHT TRAFFIC

PRODUCT	At 40°F	At 60°F	At 70°F
ELASTO-GLAZE 6001AL-HT (VOC)	1-2 hrs/8 hrs/16-24 hrs	1-2 hrs/4-6 hrs/10-12 hrs	1-2 hrs/2 hrs/4 hrs
ELASTO-GLAZE 6001AR	1-2 hrs/8 hrs/16-24 hrs	1-2 hrs/4-6 hrs/10-12 hrs	1-2 hrs/2 hrs/4 hrs